

# Residential 0.3

## TECHNICAL DATA SHEET



LVT MULTILAYER FLOORING

BY ASPECTA®

PHYSICAL PROPERTIES & PACKAGING – MODULAR MULTILAYER FLOORING 6.5MM/0.3MM	
Size	220mm x 1210mm (8.66" x 47.64")
<b>Construction:</b> Extruded Vinyl Core Top Layer Pre-Attached Underlayment	4.0mm (0.157") ISOCORE Technology® 1.5mm (0.059") Luxury Vinyl Tile (LVT) 1.0mm (0.039") HDPE
Use	Light Commercial & Residential
Wear Layer	0.3mm (12mil)
Edge Detail	Micro-Bevel Edge
Finish	Urethane with Enhanced Ceramic Bead (ECB)
Embossing(s)	Natural Timber
Thickness	6.5mm (0.256")
Pieces/Carton	7
Coverage/Piece	0.266m <sup>2</sup> (2.86 Sq.Ft.)
Coverage/Carton	1.862m <sup>2</sup> (20.02 Sq.Ft.)
Coverage/Pallet	40 Cartons (74.48m <sup>2</sup> / 801.7 Sq.Ft.)
Coverage/Container	30 Pallets (2.234,4m <sup>2</sup> / 24050.88 Sq.Ft.)
Limited Warranty	5 Year Light Commercial 10 Year Domestic

EUROPEAN / INTERNATIONAL STANDARDS – MANUFACTURING & USAGE (EN 16511)				
Description	Standard	Symbol	Requirements	Results
Classification (Level of Use)	EN ISO 10582 EN ISO 10874		<b>Commercial - Moderate (Class 31)</b> Wear Layer (Nominal): ≥0.3mm Thickness (Nominal): ≥2.0mm	Passes Requirements (Nominal)
Resistance to Staining [Grade, per Group] –	EN 438-2 (Group 1 – Only 10 Minutes)		N/A	Groups 1 and 2: Grade 5 Group 3: Grade 5
Locking Strength	ISO 24334		N/A	Long Side ≥1.0kN/m Short Side ≥1.5kN/m
Length (l)	ISO 24337		≤1500mm: Δl ≤0.5mm l >1500mm: Δl ≤0.3mm/m (Versus Nominal)	Passes Requirements
Width (w)			Δw <sub>avg</sub> ≤0.10mm (Versus Nominal) w <sub>max</sub> - w <sub>min</sub> ≤0.20mm	Passes Requirements
Squareness (q)			q <sub>max</sub> ≤0.20mm	Passes Requirements
Straightness (s)			s <sub>max</sub> ≤0.30mm/m	Passes Requirements
Thickness	ISO 24337		Δt <sub>avg</sub> ≤0.50mm (Versus Nominal) t <sub>max</sub> - t <sub>min</sub> ≤0.50mm	Passes Requirements

# Residential 0.3

## TECHNICAL DATA SHEET



Dimensional Stability Due to Variation of Temperature	EN ISO 23999		N/A	≤0.25%
Flatness (f)	ISO 24337	N/A	Maximum Single Values: f <sub>w,concave</sub> ≤0.15%, f <sub>w,convex</sub> ≤0.20% f <sub>l,concave</sub> ≤0.50%, f <sub>l,convex</sub> ≤1.00%	Passes Requirements
Openings (o)	ISO 24337	N/A	Measured from the Surface Between Vertical, Contacting Edges: O <sub>avg</sub> ≤0.15mm, O <sub>max</sub> ≤0.20mm	Passes Requirements
Height Difference (h)	ISO 24337	N/A	h <sub>avg</sub> ≤0.10mm h <sub>max</sub> ≤0.15mm	Passes Requirements
Colour Fastness to Light	ISO 105-B02, Method 2		N/A	≥Grade 6

### EUROPEAN / INTERNATIONAL STANDARDS – CE CERTIFICATION / TESTING

Description	Standard	Symbol	Requirements	Results
CE Certification	EN 14041		Refer to Standards Below	Refer to Results Below
Reaction to Fire (and Smoke Production)	EN 13501-1 EN ISO 9239-1 EN ISO 11925-2		<b>B<sub>fl</sub> - s1</b> Critical Flux: ≥8.0kW/m <sup>2</sup> Flame Spread: ≤150mm within 20s Smoke Value as % x min: ≤750	Passes Requirements
Content of PCP (Pentachlorophenol)	EN 14041		<5ppm	Passes Requirements
Formaldehyde Emission	EN 717-1		<b>Class E1:</b> Release ≤0.124mg/m <sup>3</sup>	Passes Requirements
Slip Resistance (Dry)	EN 13893		<b>Class DS:</b> Coefficient of Friction ≥0.3	Surpasses Requirements

### EUROPEAN / INTERNATIONAL STANDARDS – AUXILIARY PERFORMANCE & SAFETY

Description	Standard	Symbol	Requirements	Results
Slip Resistance (Wet)	DIN 51130	N/A	Grade R9: ≥6° and <10°	Passes Requirements
Chemical Resistance	EN ISO 26987 / EN 423		N/A	No Effect
Impact Sound Insulation <sup>1</sup>	EN ISO 10140-3 ISO 717-2 EN ISO 140-8		N/A	ΔL <sub>w</sub> = 18dB
Product-Content Safety	REACH SVHC 169	N/A	Refer to Standard	Passes Requirements
Heavy Metals	EN 71-3	N/A	Refer to Standard	Passes Requirements

# Residential 0.3

## TECHNICAL DATA SHEET



**Footnotes**

**1) Impact Sound Insulation (EN ISO 10140-3, ISO 717-2, EN ISO 140-8):**  $\Delta L_w$  = Weighted Reduction of Impact Sound Pressure Level

The manufacturing facility is ISO 9001 (Quality Management System) and ISO 14001 (Environmental Management System) certified.